

Lexan*Margard*MRA3 Sheet

Product Datasheet

Description
High abrasion resistant, non weatherable sheet.

Lexan Margard MRA3 sheet is a double-sided coated polycarbonate sheet offering excellent abrasion resistance, excellent dimensional stability, impact resistance and optical clarity, for flat applications only. Typical applications include machine guards and interior glazing.

Typical Property Values •

Property	Test Method	Unit	Value
Physical			
Density	ISO 1183	g/cm ³	1.20
Water absorption	Equilibrium	%	0.35
Mechanical			
Tensile stress, yield [¥])	ISO 527	MPa	60
Tensile modulus [¥])	ISO 527	MPa	2200
Elongation, yield [¥])	ISO 527	%	6
Elongation, break [¥])	ISO 527	%	110
Flexural strength, yield [‡])	ISO 178	MPa	100
Flexural modulus [‡])	ISO 178	MPa	2500
Thermal			
Vicat Softening Temp, Rate B /120 [‡])	ISO 306	°C	150
HDT/Be, 0.45 MPa [‡])	ISO 75/Be	°C	138
Thermal Expansion [‡])	ASTM D696	1/°C	7x10 ⁻⁵
Optical			
Light transmission (<3mm)	ASTM D1003	%	89.5
Light transmission (4-6mm)	ASTM D1003	%	86
Taber abrasion 1)			
CS-10F, 500g, 500 cycles	ASTMD1044	% haze	3

These property values have been derived from Lexan* resin data for the material used to produce this sheet product.

The target value for this property is 2-3 % however, the reproducibility of the test method between laboratories is variable in that single, individual measurements can be as high as 5%.

Coating will crack before specified value.

Property of the base sheet and/or uncoated side

Lexan and Margard are trademarks of SABIC Innovative Plastics IP BV

SABIC Innovative Plastics™



Lexan*Margard*MRA3 Sheet

Product Datasheet

Chemical Resistance

Lexan Margard MRA3 sheet has high resistance to most chemicals. In applications where it will come into contact with aggressive chemicals, specific (application related) testing of the material is strongly

Assemblina

Parts made from Lexan Margard MRA3 sheet can be assembled with plastics, metals, rubber and other materials using many types of adhesive bonding, welding and mechanical fastening techniques. Since some of these techniques can cause environmental stress cracking, please ensure that you have carried out tests regarding its suitability for your applications or end use.

Product Availability

 Product code:
 Lexan Margard, MRA3

 Standard gauge:
 1.00, 2.00, 3.00, 4.00, 6.00, mm
 Standard width: for 1.00-2.00 mm: 1220 mm; for 3.00-6.00 mm: 2000 mm

Maximum length: 3000 mm Standard colors: clear (112)



* Trademark of SABIC Innovative Plastics IP BV

Polycarbonate Sheet



ООО «Торгово-Строительная Компания Империя»

Unbreakable

109382, Россия, г.Москва, ул.Нижние поля, 31 +7(495)646-81-65 info@tbc-empire.ru www.tbc-empire.ru

LLC TBC Empire

109382, Russia, Moscow, Nizhniye polya,31 +7(495)646-81-65 info@tbc-empire.ru www.tbc-empire.ru

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT http://www.sabic-ip.com AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC Innovative Plastics is a trademark of Sabic Holding Europe BV

* Trademarks of SABIC Innovative Plastics IP BV